



13 Natal Street, Paarden Eiland, 7405
P.O. Box 498, Paarden Eiland, 7420
National: 0861 105 973
CPT: 021 510 5811
Fax: 021 510 5818
www.classiqcoatings.com
technical@classiqcoatings.com

TECHNICAL DATA SHEET

ACE COAT GLOSS WBS306

DESCRIPTION

ACE COAT GLOSS WBS306 has been specifically formulated to meet the requirements for double sided coating. ACE COAT GLOSS WBS306 is quick drying, with excellent ANTI-BLOCKING AND RELEASE CHARACTERISTICS.

FEATURES

- Rapid drying
- Excellent release
- Excellent press stability
- Good scuff resistance
- Excellent gloss

PROPERTIES

- | | |
|---------------------------|----------------------------------|
| ▪ Gloss (60°) | 50 – 60% |
| ▪ Solids Content | 34.8 ± 1.0% |
| ▪ Package Viscosity | 29 – 31 Sec DIN Cup No.4 @ 25°C |
| ▪ pH | 8.6 – 8.9 |
| ▪ Recommended Film Weight | 4 – 6 g/m ² (wet) |
| ▪ Reducer | water |
| ▪ Wash Up | water, water/alcohol or AQUAWASH |
| ▪ Flash Point | non-flammable |

DRYING

By means of infra-red drying unit.

PACKAGING AND STORAGE

Packed in 25 Kg pails or 200 Kg drums. Storage stability is six months in original, unopened containers at 20° C.

GENERAL

The components used in ACE COAT GLOSS WBS306 would be compliant with FDA regulations for indirect food contact. **WBS306 does not contain ITX (Isopropylthioxanthone), TAA (Titanium Acetylacetonate), benzophenone or 4-methyl benzophenone.**

THIS DATA SUPERCEDES ANY PREVIOUS DATA PRIOR TO NOVEMBER, 2020

