



13 Natal Street, Paarden Eiland, 7405
P.O. Box 498, Paarden Eiland, 7420
National: 0861 105 973
CPT: 021 510 5811
Fax: 021 510 5818
www.classiqcoatings.com
technical@classiqcoatings.com

TECHNICAL DATA SHEET

UV ACRYLIC SEALER MEV3009WH

DESCRIPTION

UV ACRYLIC SEALER MEV3009WH is an opaque white UV-curable woodcoating which provides a semi-gloss finish and has been specifically designed for the sealing of wooden mouldings.

FEATURES

- Fast curing
- Semi-gloss finish
- Outstanding mileage
- High opacity white coating
- High scuff and abrasion resistance
- Good adhesion to wooden substrates
- Excellent sealing properties
- Acceptable odour levels
- Low foaming
- High slip

PROPERTIES

- | | |
|---------------------------|-----------------------------------|
| ▪ Cure speed (80W) | 22 m/min |
| ▪ Relative Density @ 25°C | 1.4 – 1.6 |
| ▪ Viscosity | 30 – 32 Sec. Zahn Cup No.4 @ 25°C |
| ▪ Solids Content | 100% |
| ▪ Recommended Film Weight | 12g/m ² |
| ▪ Particle Size | <25µm |
| ▪ Gloss @ 60 degrees | 55 – 65% (Valkote Board) |
| ▪ Flashpoint | N/A |

DRYING

By means of UV curing unit.

PACKAGING AND STORAGE

Packed in 25 Kg pails or 200 Kg drums. Storage stability is six months in original, unopened containers at 20°C.

GENERAL

MEV3009WH does not contain ITX (Isopropylthioxanthone) or TAA (Titanium Acetylacetonate).

THIS DATA SUPERCEDES ANY PREVIOUS DATA PRIOR JULY, 2020

