



13 Natal Street, Paarden Eiland, 7405
P.O. Box 498, Paarden Eiland, 7420
National: 0861 105 973
CPT: 021 510 5811
Fax: 021 510 5818
www.classiqcoatings.com
technical@classiqcoatings.com

TECHNICAL DATA SHEET

UV SILKSCREEN VARNISH SUG261

DESCRIPTION

UV SILKSCREEN VARNISH SUG261 is a gloss UV overprint varnish for paper and board designed to provide a high gloss, fast curing with a smooth glass-like finish. This product is suitable for spot varnishing on laminating film with dyne level of $> 40 \text{ dyne/cm}^2$. As the dyne level of the laminating film reduces, so does the adhesion of the varnish.

FEATURES

- Excellent gloss
- Acceptable odour levels
- High scuff and abrasion resistance
- Good adhesion to a variety of substrates
- Excellent flow out and leveling
- Outstanding mileage
- Low foaming

PROPERTIES

- | | |
|----------------------------|------------------------------------|
| ▪ Relative Density at 25°C | 1.12g/ cm ³ |
| ▪ Solids Content | 100% |
| ▪ Recommended Film Weight | Recommend 160,180 or 200 mesh size |
| ▪ Viscosity | 26 – 28 Sec. Zahn Cup No. 4 @ 25°C |
| ▪ Gloss @ 60° | Not < 90 % on Printed Paper |
| ▪ Cure Speed(80 W) | 66 m/min |
| ▪ Flashpoint | N/A |

DRYING

By means of UV curing unit.

PACKAGING AND STORAGE

Packed in 25 Kg pails or 200 Kg drums. Storage stability is six months in original, unopened containers at 20°C.

GENERAL

The components used in UV SILKSCREEN VARNISH SUG261 would be compliant with FDA regulations for indirect food contact.

SUG261 does not contain ITX (Isopropylthioxanthone) , TAA (Titanium Acetylacetonate).

THIS DATA SUPERCEDES ANY PREVIOUS DATA PRIOR TO JANUARY, 2020

