



13 NatalStreet, Paarden Eiland, 7405
P.O. Box 498, Paarden Eiland, 7420
National: 0861 105 973
CPT: 021 510 5811
Fax: 021 510 5818
www.classiqcoatings.com
technical@classiqcoatings.com

TECHNICAL DATA SHEET

UV DISTELL GLOSS VARNISH VR2097

DESCRIPTION

UV DISTELL GLOSS VARNISH VR2097 is a gloss UV overprint varnish for paper and board designed to provide a high gloss and yield finish for Bag in Box (BiB) and carton work. VR2097 is suitable for roller coating application in-line on wet UV inks or off-line on dry conventional inks.

FEATURES

- Fast curing
- Excellent gloss
- Outstanding mileage
- High scuff and abrasion resistance
- Good adhesion to a variety of substrates
- Acceptable odour level
- Low foaming
- High slip

PROPERTIES

- | | |
|---------------------------|----------------------------------|
| ▪ Cure Speed (80W) | 109 m/min |
| ▪ Relative Density @ 25°C | 1.015 |
| ▪ Viscosity | 60 – 65 Sec Zahn Cup No.2 @ 25°C |
| ▪ Solids Content | 100% |
| ▪ Recommended Film Weight | 3 – 5 g/m ² |
| ▪ Gloss @ 60° | 92 – 97% (Valkraft board) |
| ▪ Angle of Slide | 16 – 19° (Coating to metal) |
| ▪ Foaming Test | < 10 % |
| ▪ Flashpoint | N/A |

DRYING

By means of UV curing unit.

PACKAGING AND STORAGE

Packed in 25 Kg pails or 200 Kg drums. Storage stability is six months in original, unopened containers at 20°C.

GENERAL

VR2097 does not contain ITX (Isopropylthioxanthone) or TAA (Titanium Acetylacetonate).

The raw materials used in VR2097 are acceptable for use under EU regulations governing hazardous materials for the packaging industry. VR2097 is not toxic but will cause taint and odour problems if in direct contact with foodstuffs, especially those of a high fat content. Therefore VR2097 should be used only in applications where the varnish does not come into direct contact with food.

THIS DATA SUPERCEDES ANY PREVIOUS DATA PRIOR TO APRIL, 2020

