



13 Natal Street, Paarden Eiland, 7405
P.O. Box 498, Paarden Eiland, 7420
National: 0861 105 973
CPT: 021 510 5811
Fax: 021 510 5818
www.classiqcoatings.com
technical@classiqcoatings.com

TECHNICAL DATA SHEET

UV INLINE FOIL GLOSS VR2130

DESCRIPTION

UV IN-LINE FOIL GLOSS VR2130 is a fast curing, gloss UV overprint varnish for in-line application to foil-laminated papers and boards and is designed to provide a high gloss and yield finish for food and label packaging. VR2130 has specially been formulated without BENZOPHENONE or 4-METHYL BENZOPHENONE and is, therefore, a low odour product. VR2130 is suitable for roller coating application in-line on wet UV inks or off-line on dry conventional inks.

FEATURES

- Low odour
- High gloss level
- Outstanding mileage
- Good adhesion to foil substrates
- High scuff and abrasion resistance
- Acceptable defoaming
- Fast curing
- High slip

PROPERTIES

- | | |
|---------------------------|-----------------------------|
| ▪ Cure Speed (80W) | 74 m/min |
| ▪ Relative Density @ 25°C | 1.015 |
| ▪ Viscosity | 60 Sec DIN Cup No.4 @ 25° C |
| ▪ Solids Content | 100% |
| ▪ Recommended Film Weight | 3 – 5 g/m ² |
| ▪ Gloss @ 60° | >90% (Valkraft board) |
| ▪ Foaming Test | <25 % |
| ▪ Flashpoint | N/A |

DRYING

By means of UV curing unit.

PACKAGING AND STORAGE

Packed in 25 Kg pails or 200 Kg drums. Storage stability is six months in original, unopened containers at 20°C.

GENERAL

The components used in UV INLINE FOIL GLOSS VR2130 would be compliant with FDA regulations for indirect food contact.

VR2130 does not contain ITX (Isopropylthioxanthone), TAA (Titanium Acetylacetonate), 4-METHYL BENZOPHENONE or BENZOPHENONE.

THIS DATA SUPERCEDES ANY PREVIOUS DATA PRIOR TO APRIL, 2020

