



13 Natal Street, Paarden Eiland, 7405
P.O. Box 498, Paarden Eiland, 7420
National: 0861 105 973
CPT: 021 510 5811
Fax: 021 510 5818
www.classiqcoatings.com
technical@classiqcoatings.com

TECHNICAL DATA SHEET

RADCOAT DIGITAL MATT PRIMER VR3308

DESCRIPTION

RADCOAT DIGITAL MATT PRIMER VR3308 is a gloss UV overprint varnish designed for digital coater application over digital inks on paper and board to provide a high yield matt finish with good scuff resistance.

FEATURES

- Fast curing
- Smooth matt finish
- Outstanding mileage
- High scuff and abrasion resistance
- Good adhesion to a wide range of digital inks*
- Acceptable odour levels
- Low foaming
- High slip

*We recommend prior testing of varnish adhesion to ink.

PROPERTIES

- | | |
|---------------------------|----------------------------------|
| ▪ Cure Speed (80W) | 40 m/min |
| ▪ Relative Density @ 25°C | 1.015 |
| ▪ Viscosity | 15 – 16 Sec Zahn Cup No.4 @ 25°C |
| ▪ Solids Content | 100% |
| ▪ Recommended Film Weight | 3 – 5 g/m ² |
| ▪ Gloss @ 60° | 40 – 45% (JAK paper) |
| ▪ Flashpoint | N/A |

DRYING

By means of UV curing unit.

PACKAGING AND STORAGE

Packed in 25 Kg pails or 200 Kg drums. Storage stability is six months in original, unopened containers at 20°C.

GENERAL

VR3308 does not contain ITX (Isopropylthioxanthone) or TAA (Titanium Acetylacetonate).

The components used in RADCOAT DIGITAL MATT PRIMER VR3308 would be compliant with FDA regulations for indirect food contact.

THIS DATA SUPERCEDES ANY PREVIOUS DATA PRIOR TO APRIL, 2020

